

Environmental Certification Scheme



Carpet Name: YUTAKA SERIES

Licensee: NOLAN.UDA P/L
Licence Number: 1307
Label Number: 13177

Certification Approved: 28/11/2013

Level: 3

ACCS Contract Grading: CHD 3*
ACCS Residential Grading: NONE
Suitable for Stairs: Yes

Date Printed: 28/11/2013

Allan Firth



Allan Firth
Secretary ACCS



Administered by the Carpet Institute of Australia Limited ABN 11 006 829 303
PO Box 7172, St Kilda Road, Melbourne Victoria 8004 Tel: (03) 9804 5559 • Fax: (03) 9804 5560
Email: info@carpetoz.com.au • www.carpetinstitute.com.au

This certificate remains the property of the Carpet Institute of Australia Limited.

Carpet Details:

Company: NOLAN.UDA P/L
Licence No: 1307

Label No: 13177
Office No: 5758

Names:

YUTAKA SERIES

Details:

Awarded Res Grade: NONE
 Awarded Con Grade: CHD 3*
 Registered On: 20/09/2013
 Active: Yes
 Date In-Active:
 Manufacture Method: Tufted
 Twist Set: N/A
 Dyeing Method: Melt Dyed
 #Colours/Designs: 6
 Backing Type: Other
 Felted: N/A
 Spinning System: BCF
 Insect Resist Agent: N/A
 Master Product:

Test Results:

Pile Mass g/m² (oz/yd²): 498 (14.7)
 SPM g/m² (oz/yd²): 362 (10.7)
 Stated Pile Height (mm): 3.0
 Minimum Pile Height (mm): 0.0
 Maximum Pile Height (mm): 0.0
 Dynamic Loading Loss (%): 18.8
 Static Loading Loss (%): 3.1
 Tex (g/1000m): 206
 Measured Pile Thickness (mm): 3.2
 Machine Gauge (Tufts/dm): 39.4
 Meas Tufts Perp to Selvege: 39.2
 Meas Tufts Para to Selvege: 52.9
 Treated For Soiling Resistance: Yes
 Flouro Carbon Treated: Yes
 Stain Resist Chem Treated: No

Hexapod Scores:

	Text Chng	Wrst Angl	Col Chng	Wrst Angl	Loss (mm)	Loss (%)
1500:	4.5	4.0	4.5	4.0	0.2	6.3
8000:	2.5	2.5	3.5	3.5	0.9	28.1

Quality Assurance Test:

Cut Pile (%): 0
 Loop Pile (%): 100
 Panel Assessment Contract: 14
 Panel Assessment Residential: 14
 Suitable For Stairs: Yes
 Tile: Yes SheetGoods: No
 Fibre Signature: NBA:100

ACCS Test:

	Con	Res	Max
SPM/PH Ratio:	12	16	16
Volume Density:	11.4	11.4	20
Tuft Density:	9	9	9
Dyn Load:	4	4	5
Stat Load:	5	5	5
Soiling Prop:	13	13	16
Abraison Res:	9.2	9.2	10
Sub Total:	63.6	67.6	81
Panel Assess:	14	14	19
Total:	77.6	81.6	100
Calc Residential Grade:	REHD1		5*
Calc Contract Grade:	CMD		2*

Calculations

Pile Height(mm): 4.2
 Tuft Density(per dm²): 2073.7
 GSPM(g/m²): 415.0
 GSPM (abrasive) (g/m²): 275.0
 Soiling Propensity: 12.0 +1.0

OAF Values

OAF: 3.9
 Calc Density (+-5%): 0.11 0.113 0.12
 Base Fibre: NYLON
 Benchmarks:
 RHD1 0 RHD2 3.5
 REHD1 3.5 REHD2 3.5

Environmental Classification:

ECS: Yes
 Level: 3

	Calc	B/M	P/F
Acoustic:	3.2	3	PASS
Thermal:	28.3	15	PASS
VOC:			
TVOC	0		

Notes:

20/9/13 Submitted by S Gilbertson. 25/9/13 Tex confirmed at 206 so grading not changed.
 Panel awarded CHD(S) 3*. 28/11/13 Panel certified ECS Level 3.