

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTa Product Testing
A.B.N. 43 006 014 106
1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O. Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

CLIENT : NOLAN UDA PTY LTD
3 BRADFORD STREET
ALEXANDRIA NSW 2015

TEST NUMBER : 7-585262-CN
ISSUE DATE : 04/06/2012
PRINT DATE : 04/06/2012
ORDER NUMBER : 120523
ORDER NUMBER : 120523

SAMPLE DESCRIPTION "Capri Vinyl Fabric"
Vinyl coated fabric
Colour: Blue

IMO RESOLUTION
A.652 (16)
19 OCTOBER 1989

Recommendation on fire test procedures for upholstered
furniture

SECTION 8.2
(MODIFIED)

Smouldering cigarette test
Test conditions: Temp: 21 degC
Relative Humidity: 49 %

Ignition did not occur

Extent of Damage	Vertical	Horizontal	
Length:	0	0	mm
Width:	0	0	mm
Depth:	0	0	mm

Test assembly self extinguished
Test assembly was/was not found to be smouldering
when dismantled

Camel plain cigarettes used with a smouldering rate of
8+/-2min over 40mm

Submitted sample Complies



AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTa Product Testing
A.B.N. 43 006 014 106
1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O. Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

CLIENT : NOLAN UDA PTY LTD
3 BRADFORD STREET
ALEXANDRIA NSW 2015

TEST NUMBER : 7-585262-CN
ISSUE DATE : 04/06/2012
PRINT DATE : 04/06/2012
ORDER NUMBER : 120523
ORDER NUMBER : 120523

IMO RESOLUTION
A.652 (16)
19 OCTOBER 1989
SECTION 8.3

Recommendation on fire test procedures for upholstered furniture

Flame Test

Test conditions: Temp: 21 degC
Relative Humidity: 48 %

Extent of damage	Vertical	Horizontal	
Length:	28	10	mm
Width:	10	6	mm
Depth:	0	0	mm

dismantled

Note: Propane/Butane gas used as ignition source

Submitted sample: Complies

