

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400

TEST REPORT

Client : Nolan UDA Pty Ltd
3 Bradford Street
Alexandria NSW 2015

Test Number : 20-004562
Issue Date : 7/10/2020
Print Date : 8/10/2020
Order Number : 200903

Sample Description Clients Ref : "GA100W - Sand Bank II - GA1855W/GA1853W"
Loop pile carpet tiles
Colour : Various
End Use : Flooring
Nominal Composition : Nylon with PVC backing
Nominal Mass per Unit Area/Density : Approx 4.48kg/m2
Nominal Thickness : Approx 6mm

AS ISO 9239.1-2003

Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source

Date of Sample Arrival 09/02/2020

Date Tested 07/10/2020

CHF Value	1	2	3	Mean
Length	3.4	-	-	- kW/m ²
Width	3.0	3.2	2.4	2.9 kW/m ²

HF-30 Value	1	2	3	Mean
Length	5.1	-	-	- kW/m ²
Width	4.3	4.4	4.0	4.2 kW/m ²

Smoke Value	1	2	3	Mean
Length	490	-	-	- %.min
Width	476	424	491	464 %.min

Melting Yes

Penetration of flame through to substrate Yes

216959

46466

Page 1 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

APPROVED SIGNATORY



MICHAEL A. JACKSON B.Sc. (Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400

TEST REPORT

Client : Nolan UDA Pty Ltd
3 Bradford Street
Alexandria NSW 2015

Test Number : 20-004562
Issue Date : 7/10/2020
Print Date : 8/10/2020
Order Number : 200903

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of $23\pm 2^{\circ}\text{C}$ and relative humidity of $50\pm 5\%$ for a minimum of 48 hours prior to testing.

Results in accordance with section 8.4 have not been included in the report. They are available upon request.

Each specimen was adhered to a substrate of 6mm thick fibre reinforced cement board using Roberts 656 adhesive and clamped prior to testing.

216959

46466

Page 2 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



A handwritten signature in blue ink, likely belonging to Michael A. Jackson.

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR