

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106


1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

## **TEST REPORT**

Client :	Nolan UDA Pty Ltd		
	3 Bradford Street		
	Alexandria NSW 2015		

Test Number :	23-002489
Issue Date :	29/06/2023
Print Date :	29/06/2023
Order Number :	230620

Sample Description	Clients Ref : "Atlas Type 1"			
	Coated woven fabric			
	Colour : White			
	End Use : Outdoor Tension Structure			
	Nominal Composition : PVC			
	Nominal Mass per Unit Area/Density :	700g/m2		
	Nominal Thickness : <1mm			



298267

65249

C Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

1. Chris Campbell

Chris Campbell APPROVED SIGNATORY



Page 1 of 2

MICHAEL A. JACKSON B.Sc.(Hons)

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

## **TEST REPORT**

Client :	Nolan UDA Pty Ltd	Test Number :	23-002489	
	3 Bradford Street	Issue Date :	29/06/2023	
	Alexandria NSW 2015	Print Date :	29/06/2023	
		Order Number :	230620	

AS 1530.2-1993

Methods for Fire Tests on Building Materials, Components and Structures. Part 2: Test for Flammability of Materials

Date Tested			29-06-2023	
Flammability Index			1	
		Length	Width	
Spread Factor		0	0	
Heat Factor		1	1	
Maximum height (d)				
Mean		2.2	2.7	
Coefficient of Variation		11.9	9.7	%
Heat (a)				
Mean		1.5	1.5	°C.min
Coefficient of Variation		0.0	0.0	%
Number of Specimens Teste	ed	6	6	
Observation	Visible smoke			

These test results relate only to the behaviour of the test specimens of the material under the particular conditions of the test, and they are not intended to be the sole criterion for assessing the potential fire hazard of the material in use.

298267

65249

C Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

Chris Campbell





AICHAEL A. JACKSON B.Sc.(Hons)